



SUNCO CHEMICALS LIMITED

65 Latkrabang Industrial Estate , Chalongkrung Rd. Latkrabang ,
Bangkok 10520 Tel. 02-3260559 - 60

2K POLY-PUTTY OTOMO

DESCRIPTION :

2K POLY-PUTTY OTOMO is a two component polyester base putty, made of a special unsaturated polyester resin which is cure at room temperature with cyclohexanone peroxide as a hardener. It dries quickly and easy to sand with excellent adhesion.

It is suitable for the filling of cavities and rotten area of metallic surfaces and fiberglass.



PHYSICAL PROPERTIES :

| | | |
|--------------------------------|---|---|
| Appearance | : | Slightly yellow paste |
| Specific Gravity | : | 1.70 ± 0.10 |
| Mixability | : | Good |
| Gel Time (30 ^o C) | : | 2 - 4 Mins. (After mixing hardener) |
| Sanding Time | : | 20 - 40 Mins. |
| Workability | : | Excellent |
| Sandability | : | Excellent |
| Heat Resistance | : | Passed (65 ± 2 ^o C, 48 Hrs.) |
| Storage Period | : | 6 Months after manufacturing. |

HARDENER :

Yellow paste of Cyclohexanone peroxide

MIXING RATIO :

100 Parts of POLY-PUTTY : 2 Parts of Hardener

APPLICATION :

Apply on metal surface with putty knife. Do not apply putty thick at one coat.

SURFACE PREPARATION :

The surface must be thoroughly clean, remove rust, grease and dirt, ensure the surface is dry and sand smooth with coarse sand paper.